



BISCO[®] Silicones

High Performance Foams Division
 171 West St. Charles Road
 Carol Stream, IL 60188
 Tel: 860.237.2068 / Fax: 860.784.6201
 www.rogerscorporation.com

Typical Product Properties

Typical and Maximum Allowed Values for Density of Cellular Silicones

	Pounds Per Cubic Foot						
	EP-2022	BF-1000	HT-870		HT-800	HT-820	HT-840
Typical ¼"	10.5	12.5	15.5		20.5	23.5	27.5
Max Allowed	11.5	14.4	Black 19.1	Red 20.4	29.5	33.0	33.5
	Kilograms Per Cubic Meter						
Typical ¼"	168.2	200.3	248.3		328.4	376.5	440.6
Max Allowed	184.2	230.7	306.0		472.6	528.7	536.7

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.

BISCO is a licensed trademark of Rogers Corporation.
 © 2003 Rogers Corporation, Printed in U.S.A. All rights reserved.
 3085-1003-0.4C, Publication #180-080