

BISCO® HT-6360 Flame Retardant Liquid Silicone Rubber Sheetting (65 Durometer)

PHYSICAL PROPERTY		TYPICAL VALUE	TEST METHOD
Durometer, Shore "A" (pts)		65	ASTM D 2240
Tensile Strength, psi (MPa)		300 (2.1)	ASTM D 412
Elongation, %		175	ASTM D 412
Tear Strength, ppi (kN/m)		50 (8.7)	ASTM D 624
Compression Set, % 70 hr @ 302°F (150°C)		35	ASTM D 395 (B)
LOI Index		55	ASTM D 2863
Surface Flammability		<10	ASTM E 162
Rate of Smoke Generation	Specific Optical Density @ 1.5 minutes flaming mode	<5	ASTM E 662
	Specific Optical Density @ 4.0 minutes flaming mode	<30	ASTM E 662
Toxic Gas Production		Meets Requirements	Bombardier SMP 800 C
Flammability		V-0	UL 94
Color		Black	N/A

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.